

## Product Data Sheet

**DIAION™ SAF10DL**

DIAION™ SAF10DL is a gel type strongly basic anion exchange resin. It has a higher cross-linkages and low-odor and low leachable properties. A wide range of applications, especially in a field of manufacturing drinking water and refining sugar liquors, is recommended.

**Product**

Grade Name	DIAION™ SAF10DL	
Type	Strong Base Anion	
Matrix	Styrene-DVB, Gel	
Functional Group	Type I (trimethyl ammonium groups)	
Ionic Form	Cl <sup>-</sup>	

**Specification**

Whole Bead Count	-	90 min.
Salt Splitting Capacity	meq/mL	1.3 min.
Water Content	%	39 - 47
Particle Size Distribution on 1180 μm	%	5 max.
Particle Size Distribution thr. 500 μm	%	1 max.
Effective Size	mm	0.50 min.
Uniformity Coefficient	-	1.6 max.
ΔTOC	ppb	200 max.

**Typical Properties**

Shipping Density	g/L	690
Mean Particle Size	μm	670
Particle Density (Cl <sup>-</sup> )	g/mL	1.08
Total Swelling (Cl <sup>-</sup> to OH <sup>-</sup> )	%	22

**Recommended Operating Conditions**

Maximum Operating Temperature	°C	80 (Cl <sup>-</sup> ) 60 (OH <sup>-</sup> )
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	m/h	10 - 60
Regenerant		NaOH
Regenerant Concentration	%	NaOH 2 - 8
Regenerant Level	g/L	50 - 200
Regenerant Flow Rate	m/h	2 - 8
Total Rinse Requirement	BV	2 - 10


**Biokal**

© +31529485928


 info@biokal.com  
<https://www.biokal.com>

**MITSUBISHI  
CHEMICAL**

### Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION™ SAF10DL (Cl form) resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of SAF10DL




Fig. 2 Bed Expansion of SAF10DL

### Notice

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.



**Biokal**

Chromatography & Purification Solutions

☎ +31529485928



info@biokal.com  
<https://www.biokal.com>



**MITSUBISHI  
 CHEMICAL**